


### LOW PRESSURE POLYURETHANE FOAM INFORMATION

<b>Description</b>	Medium density, closed-cell, two-component Pour in place polyurethane foam
<b>PIP</b>	Pour in Place
<b>Applications</b>	Designed to be used in concrete lifting, leveling, designed to fill cavities, holes, or voids and soil stabilization. The foam can be dispensed into clean and dry voids of various size to fill, seal, insulate, strengthen, increase load bearing capacity below the surface.
<b>Preparation for use</b>	Substrate must be clean, dry, firm, free of loose particles, and free of dust, grease and mold release agents. Protect surfaces not to be foamed. No idea for applications with high levels of water present. For additional information go to <a href="http://www.handifoam.com">www.handifoam.com</a>
<b>Use</b>	Condition chemical to 65-90°F (18-32°C). Follow instructions for set-up found in the operating instructions. Must be processed with HANDIFOAM HVLP GEO 3.0 A-side and HANDIFOAM HVLP GEO 3.0 (B-SIDE).
<b>PPE</b>	 <p>Recommend using in a well-ventilated area with certified respiratory protection or a powered air purifying respirator (PAPR). Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Read all instructions and SDS (Section 8) prior to use of any product.</p>
<b>Note</b>	FOR PROFESSIONAL USE ONLY. Always check the local building code before use. Cured polyurethane foam is non-toxic and inert.
<b>Temperature Guidelines</b>	Please see chart located on page 2
<b>Shelf-life</b>	6 months (When stored unopen at 50-80F)
<b>Compatibility</b>	Cured low pressure polyurethane foam is chemically inert and non-reactive in approved applications, and will not harm electrical wire insulations, extruded polystyrene foams, Romex®, rubber, PVC, polyethylene (i.e. PEX) or other plastics. The product is not resistant to UV rays; if left exposed the product should be coated or painted.

TECHNICAL DATA	STANDARD	RESULTS
<b>Density</b>	ASTM D1621	3.0 lbs/ft <sup>3</sup> (48 kg/m <sup>3</sup> )
<b>K-factor</b>	ASTM C518	
Initial		0.165 BTU·inch/ft <sup>2</sup> ·h·2°F at 1 inch
<b>R-Value</b>	ASTM C518	6.0/in at 1-inch thickness
Initial		
<b>Compressive Strength</b>	ASTM D1622	35-40 lbf/in <sup>2</sup> (241- 276 kPa) Parallel
<b>Dimensional Stability</b>	ASTM D2126	
158°F (70°C)/ 97% RH/28 Days		2.0%
<b>Closed-Cell Content</b>	ASTM D6226	>92.0%
<b>Tumbling Friability</b>	ASTM C241	0.5-2.0
<b>Tensile Strength</b>	ASTM D1623	32 lbf/in <sup>2</sup> (193 kPa)
<b>Tack Free Time</b>	Tack Free Time	120-130 Seconds
<b>Water Absorption</b>	ASTM D2842	0.01%
<b>Resin- Specific Gravity 25C</b>	ASTM D 1638	1.165
<b>Resin- Viscosity @ 25C</b>		500 cps

**TEMPERATURE GUIDELINES**

<b>Chemical Storage Temperature</b>	Optimum 65-90°F (18-32°C); Storage outside of these ranges can shorten shelf life
<b>Outside Application Temperature</b>	32-120°F (0-49°C)
<b>Process Core Chemical Temperature</b>	75-115°F (23-46°C)
<b>Initial Drum Temperature</b>	75°F (24C)
<b>Surface Temperature (Substrate)</b>	32-190°F (0-87°C)

**EQUIPMENT SETTING GUIDELINES**

<b>HANDIFOAM HVLP GEO 3.0 A-side &amp; HANDIFOAM HVLP GEO 3.0 B-side Foam Processing</b>
<b>Equipment: Nitrosys Plus</b>
Chemical Temperature Set-Point 105 - 110°F (40 – 43°C)
Hose Temperature Set-Point 105 - 110°F (40 – 43°C)

S

**Always read all operating, application and safety instructions before using any products.** Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release ICP Building Solutions Group of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call ICP Building Solutions Group 1 330.753.4585 or 1 800.321.5585.

**NOTE:** Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. This information supersedes all previously published data. The Customer is responsible for deciding whether products and associated TDS information are appropriate for customer's use.

**Performance and actual physical properties will vary with differences in application/process equipment. The above information is based on using HandiFoam HVLP A-side, HandiFoam HVLP GEO 3.0 B-side and Nitrosys Plus at the recommended process temperatures and settings. Odor level of Spray Polyurethane foam is dependent on proper application using the recommended processing parameters and proper ventilation. Large masses of SPF should be removed to an outside safe area, cut into smaller pieces, allowed to cool before being placed into a disposal container.**

ICP low pressure one-component polyurethane foam sealants and adhesives (OCF), low pressure spray polyurethane foams (SPF), and low pressure pour-in-place polyurethane foams (PIP) are composed of a diisocyanate, hydrofluorocarbon or hydrocarbon blowing agent, and polyol. For polyurethane foam sealants/adhesives: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well-ventilated area. Avoid breathing vapors. Read the SDS and instructions carefully before use ([www.handifoam.com](http://www.handifoam.com)). For spray polyurethane foams and pour-in-place polyurethane foams: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Use only in a well-ventilated area and with certified respiratory protection or a powered air purifying respirator (PAPR). Additional information on ventilation can be found in the Product Stewardship Guide ([www.handifoam.com](http://www.handifoam.com)). Read the SDS ([www.handifoam.com](http://www.handifoam.com)) and instructions carefully before use. The urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat about 240°F (116°C). Refer to each product's TDS for specifications, testing results, and other attributes. The customer is ultimately responsible for deciding whether products and associated TDS information are appropriate for customer's use. Refer to the products' SDS, ICP Building Solutions Group's Product Stewardship Guidelines, and operating instructions for guidance on the safe and proper application of the product ([www.handifoam.com](http://www.handifoam.com)). For professional use only. Building practices unrelated to materials can lead to potential mold issues. Material suppliers cannot provide assurance that mold will not develop in any specific system.

**WARNINGS:** Follow safety precautions and wear protective equipment as recommended. Prolonged inhalation exposure may cause respiratory irritation/sensitization and/or reduce pulmonary function in susceptible individuals. Onset may be delayed. Pre-existing respiratory conditions may be aggravated. We recommend that the product is used in a well-ventilated area and with certified respiratory protection. NIOSH approved positive pressure supplied air respirator is recommended if exposure guidelines may be exceeded. Contents may be very sticky and irritating to skin and eyes, therefore wear safety glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure when operating. If liquid chemical comes in contact with skin, first wipe thoroughly with dry cloth, then rinse affected area with water. Wash with soap and water afterwards and apply hand lotion if desired. If liquid comes in contact with eyes, immediately flush with large volume of clean water for at least 15 minutes and get medical help at once. If liquid is swallowed, get immediate medical attention. Do not induce vomiting. If breathing is difficult, give oxygen. If breathing has stopped give artificial respiration. Products manufactured or produced from these chemicals are organic and, therefore, combustible. Each user of any product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage. **KEEP OUT OF REACH OF CHILDREN.**

**LIMITED WARRANTY and LIMITATION OF DAMAGES:** ICP Building Solutions Group warrants only that the product shall meet ICP Building Solutions Group specifications for the product when shipped by ICP Building Solutions Group. NO OTHER EXPRESSED OR IMPLIED WARRANTIES APPLY AND ANY IMPLIED WARRANTIES OF MERCHANTABILITY, NON-INFRINGEMENT OUTSIDE THE U.S. AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. Buyer and users assume all risks of use, handling and storage of the product. Failure to strictly adhere to any recommended procedures shall release ICP Building Solutions Group from all liability. The user of the product is responsible to determine suitability of the product for the particular use. The exclusive remedy as to any breach of warranty, negligence or other claim is limited to the replacement of the product. Liability for any indirect, incidental or consequential damage or loss is specifically excluded.



2775 Barber Road | Norton, OH 44203  
330-753-4585 | [www.icpgroup.com](http://www.icpgroup.com)

**MADE IN USA**  
WITH GLOBALLY SOURCED MATERIALS